

# TRAIDAMID® G OIL (PA6 C + OIL lubricant)

**Density** 1,14 g/cm<sup>3</sup>

**Colour** Yellow/green opaque

**Chemical Designation** PA6 C ( Cast polyamide 6)

PROPERTIES	RESULT	UNIT	PARAMETER	NORM USED
<b>Mechanical properties</b>				
Modulus of elasticity	3200	MPa	1 mm/min	DIN EN ISO 527-2
Tensile strength	76	MPa	50 mm/min	DIN EN ISO 527-2
Tensile strength at yield	76	MPa	50 mm/min	DIN EN ISO 527-2
Elongation at yield	14	%	50 mm/min	DIN EN ISO 527-2
Elongation at break	18	%	50 mm/min	DIN EN ISO 527-2
Flexural strength	103	MPa	2 mm/min , 10 N	DIN EN ISO 178
Modulus of elasticity (flex test)	3100	MPa	2 mm/min , 10 N	DIN EN ISO 178
Compression strength	18 / 35	MPa	1% / 2%. 5 mm/min , 10 N	EN ISO 604
Compression modulus	2500	MPa	5 mm/min , 10 N	EN ISO 604
Impact strength (Charpy)	No break	Kj/m <sup>2</sup>	Max. 7,5j	DIN EN ISO 179-1EU
Notched Impact stren. (Charpy)	4	Kj/m <sup>2</sup>	Max. 7,5j	DIN EN ISO 179-1EU
Ball indentation hardness	160	MPa		ISO 2039-1
<b>Thermal properties</b>				
Glass transition temperature	45	°C		DIN 53765
Melting temperature	218	°C		DIN 53765
Service temperature	130	°C	Short term	
Service temperature	100	°C	Long term	
Thermal expansion	11	10 <sup>-5</sup> K <sup>-1</sup>	23-60°C long	DIN EN ISO 11359-1;2
Thermal expansion	12	10 <sup>-5</sup> K <sup>-1</sup>	23-100°C long	DIN EN ISO 11359-1;2
Specific heat	1,7	J/(g·K)		ISO 22007-4:2008
Thermal conductivity	0,38	W/(K·m)		ISO 22007-4:2008
<b>Electrical properties</b>				
Surface resistance	10 <sup>14</sup>	Ω		DIN IEC 60093
<b>Miscellaneous properties</b>				
Water absorption	0,2 / 0,3	%	24h / 96h (23°C)	DIN EN ISO 62
Resistance to hot mater / bases	(+)			
Resistance to weathering	-			
Flammability (UL94)	HB		According to	DIN IEC 60995-11-10

## MAIN CHARACTERISTICS

High mechanical load properties  
 Electrically insulating  
 Resistant to many greases, oils and fuels  
 High toughness  
 Good slide and wear resistance

## INDUSTRY APPLICATIONS

Heavy duty industry  
 Conveyor technology  
 Textile industry  
 Mining industry  
 Mechanical engineering

Notice: The information given was made with our knowledge indicating our product's possible applications. Existing commercial patents must be observed. These values represent averages taken from samples, so we reserve the right of technical alterations. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.traidvillarroya.com](http://www.traidvillarroya.com). Traidamid, TKG and TVH as well as their logos are registered trademarks of the Traid Villarroya group of companies, in Europe and other countries.